



Lion Elastomers LLC

1615 Main Street • P.O. Box 667 • Port Neches, TX 77651
800 / 535-9960 • www.lionelastomers.com

SBR 1011AE Elastomer

Product Data

Hot polymerized SBR 1011AE elastomer is recommended for adhesives, pressure sensitive tape and label, and mechanical rubber goods applications where non-staining and high tack is essential.

Unique Features

- ▶ Hot polymerized styrene-butadiene elastomer
- ▶ Broad molecular weight makes dissolving easier
- ▶ Light color

Applications

- ▶ General purpose, tape, and label adhesives
- ▶ Mechanical rubber goods and bead wire

Typical Properties

<u>Property</u>	<u>Test Method*</u>	<u>Typical</u>
Mooney viscosity, MML 1+4 (100°C)	—	50 - 58
Bound Styrene, Weight %	—	22.5 – 24.5
Organic acid, Weight %	—	4.5 – 6.5
Soap, Weight %	—	0.5 Max.
Ash, Weight %	—	1.5 Max.
Volatile matter, Weight %	ZS 1008K	0.75 Max.
Emulsifier	—	Rosin acid
Coagulant	—	Acid
Stabilizer	—	Non-Staining
Specific gravity, g/cc (bale).....	ASTM D-792	0.94
Color	—	Off White
Physical form**, lbs/bale	—	70.0 (32 kg)

SBR 1011AE elastomer is used for adhesives, pressure sensitive tape and label, and mechanical rubber goods applications.

* Company Test Methods

** This product is available in 70 lb rectangular bales individually wrapped in 1.5 mil, low melting point film and shipped in two cell cardboard containers.

Note: Antioxidant is added to this polymer to provide protection during manufacture and storage. The end user's process may require additional antioxidant protection.

SBR 1011AE Elastomer

Rheometric Properties (MDR 2000 rheometer)

<u>Property</u>	<u>Result</u>
M _L lbf-in	0.7 – 2.7
dN-m	0.8 – 3.1
M _H lbf-in	11.0 – 15.0
dN-m	12.4 – 17.0
t _s 1, minutes	4.4 – 7.4
t' 50, minutes	9.5 – 13.5
t' 90, minutes	15.6 – 20.6

<u>MRG Starting Point Formulation</u>	<u>Weight</u>	<u>Reference Material</u>
SBR 1011AE elastomer	100.0	
Zinc oxide	3.0	IRM 91A
Sulphur	1.75	NIST SRM 371
Stearic acid	1.0	NIST SRM 372
Oil furnace black	50.0	IRB #8
TBBS	1.00	NIST RM 8384

SBR 1011AE elastomer is hot polymerized SBR polymer recommended for adhesive and pressure sensitive tape and label applications, and mechanical rubber goods applications.

Notice: All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.